





# VAPPRO VCI-849 I.V. WATER SOLUBLE VCI POWDER

## NATO STOCK NUMBER: PENDING

Conforms to MIL-I-22110C

#### **OVERVIEW**

Vappro VCI-849 is a water-soluble V.C.I. powder with superior corrosion inhibitor for wet or dry corrosion protection of ferrous metals and aluminum.

Vappro VCI-849 offers low dosage effectiveness as a treatment for closed loop cooling system, hydrotesting and wide variety of marine process applications.

#### **AREA OF USE**

- Vappro VCI-849 powder is used for wet protection of internal cavities and voids that can be covered or closed after application.
- For protection of closed loop cooling systems-dry lay-up.
- For protection of pipes and equipment during hydrostatic testing.
- For protection of tubular structures, pipes, heat exchangers, tanks, vessel etc.

Passed German VIA (Vapour Inhibition Ability) Test TL 8135-002

#### **ADVANTAGES**

- Wet corrosion protection.
- Low dosage, provides economical treatment.
- Water soluble for easy application.
- Provides effective corrosion protection against aggressive attack from chloride, salt water and other dissolved halogens.
- Biodegradable.
- Does not contain phosphates, chromates or other heavy metals.






























#### **METHOD OF APPLICATION**

#### **WET APPLICATION**

Vappro VCI-849 should be added at 0.75% by weight of water for severe applications and 0.25% by weight of water for less corrosive environment.

#### **DRY APPLICATION**

Applying powder by dusting, fogging or sprinkling. After application seal all vents.

Fogging can be achieved by using a low pressure air hose and sandblast cup.

For powder application, use 9 to 10 grams of VAPPRO VCI-849 per cubic foot (28 litres) of enclosed space. The dosage can be increased as needed for more severe conditions.

#### **METHOD OF REMOVAL**

When required, VAPPRO VCI-849 in powder form can be easily removed by using a low pressure air gun or by a water rinse.

#### **SPECIFICATIONS**

Appearance Pearl White Powder

Melting Point 260 °C

Real Density 2.17

pH at 1% solution 20 °C 7.5

 $H_2O$  wt. % > 0.05

#### **AVAILABLE PACKAGING**

25 kg & 100 kg Drum

### Magna

#### Magna International Pte Ltd

10H, Enterprise Road, Singapore 629834.

**Tel** (65) 6786-2616 **Fax** (65) 6785-1497

**Email** info@magnachem.com.sg info@vapprovci.com

Web http://www.vapprovci.com

#### Headquarters



Singapore

Regional Offices



Australia



Follow us on social media for regular updates and news.



https://www.facebook.com/vapprovci/ https://www.facebook.com/MagnaInternationalPteLtd/

The details of our products are given completely free of undertaking. Since their application lies outside our control, we cannot accept any liability for the results. User shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.







